

6. ATOMIC AND NUCLEAR PROPERTIES OF MATERIALS

Table 6.1. Revised April 1998 by D.E. Groom (LBNL). Gases are evaluated at 20°C and 1 atm (in parentheses) or at STP [square brackets]. Densities and refractive indices without parentheses or brackets are for solids or liquids, or are for cryogenic liquids at the indicated boiling point (BP) at 1 atm. Refractive indices are evaluated at the sodium D line. Data for compounds and mixtures are from Refs. 1 and 2.

Material	Z	A	$\langle Z/A \rangle$	Nuclear collision length λ_T {g/cm ² }	Nuclear a interaction length λ_I {g/cm ² }	$dE/dx _{\min}^b$ { $\frac{\text{MeV}}{\text{g/cm}^2}$ }	Radiation length X_0 {g/cm ² }	$\{X_0\}$ {cm}	Density {g/cm ³ } {g/ℓ} for gas	Liquid boiling point at 1 atm(K)	Refractive index n {(n-1)×10 ⁶ } for gas
H ₂ gas	1	1.00794	0.99212	43.3	50.8	(4.103)	61.28 ^d	(731000)	(0.0838)[0.0899]		[139.2]
H ₂	1	1.00794	0.99212	43.3	50.8	4.045 ^e	61.28 ^d	866	0.0708	20.39	1.112
D ₂	1	2.0140	0.49652	45.7	54.7	(2.052)	122.4	724	0.169[0.179]	23.65	1.128 [138]
He	2	4.002602	0.49968	49.9	65.1	(1.937)	94.32	756	0.1249[0.1786]	4.224	1.024 [34.9]
Li	3	6.941	0.43221	54.6	73.4	1.639	82.76	155	0.534		—
Be	4	9.012182	0.44384	55.8	75.2	1.594	65.19	35.28	1.848		—
C	6	12.011	0.49954	60.2	86.3	1.745	42.70	18.8	2.265 ^f		—
N ₂	7	14.00674	0.49976	61.4	87.8	(1.825)	37.99	47.1	0.8073[1.250]	77.36	1.205 [298]
O ₂	8	15.9994	0.50002	63.2	91.0	(1.801)	34.24	30.0	1.141[1.428]	90.18	1.22 [296]
F ₂	9	18.9984032	0.47372	65.5	95.3	(1.675)	32.93	21.85	1.507[1.696]	85.24	[195]
Ne	10	20.1797	0.49555	66.1	96.6	(1.724)	28.94	24.0	1.204[0.9005]	27.09	1.092 [67.1]
Al	13	26.981539	0.48181	70.6	106.4	1.615	24.01	8.9	2.70		—
Si	14	28.0855	0.49848	70.6	106.0	1.664	21.82	9.36	2.33		3.95
Ar	18	39.948	0.45059	76.4	117.2	(1.519)	19.55	14.0	1.396[1.782]	87.28	1.233 [283]
Ti	22	47.867	0.45948	79.9	124.9	1.476	16.17	3.56	4.54		—
Fe	26	55.845	0.46556	82.8	131.9	1.451	13.84	1.76	7.87		—
Cu	29	63.546	0.45636	85.6	134.9	1.403	12.86	1.43	8.96		—
Ge	32	72.61	0.44071	88.3	140.5	1.371	12.25	2.30	5.323		—
Sn	50	118.710	0.42120	100.2	163	1.264	8.82	1.21	7.31		—
Xe	54	131.29	0.41130	102.8	169	(1.255)	8.48	2.40	2.953[5.858]	165.0	[701]
W	74	183.84	0.40250	110.3	185	1.145	6.76	0.35	19.3		—
Pt	78	195.08	0.39984	113.3	189.7	1.129	6.54	0.305	21.45		—
Pb	82	207.2	0.39575	116.2	194	1.123	6.37	0.56	11.35		—
U	92	238.0289	0.38651	117.0	199	1.082	6.00	≈0.32	≈18.95		—
Air, (20°C, 1 atm.), [STP]			0.49919	62.0	90.0	(1.815)	36.66	[30420]	(1.205)[1.2931]	78.8	(273) [293]
H ₂ O			0.55509	60.1	83.6	1.991	36.08	36.1	1.00	373.15	1.33
CO ₂			0.49989	62.4	89.7	(1.819)	36.2	[18310]	[1.977]		[410]
Shielding concrete ^g			0.50274	67.4	99.9	1.711	26.7	10.7	2.5		—
Borosilicate glass (Pyrex) ^h			0.49707	66.2	97.6	1.695	28.3	12.7	2.23		1.474
SiO ₂ (fused quartz)			0.49926	66.5	97.4	1.70 ⁱ	27.05	12.3	2.20 ^j		1.458
Dimethyl ether, (CH ₃) ₂ O			0.54778	59.4	82.9	—	38.89	—	—	248.7	—
Methane, CH ₄			0.62333	54.8	73.4	(2.417)	46.22	[64850]	0.4224[0.717]	111.7	[444]
Ethane, C ₂ H ₆			0.59861	55.8	75.7	(2.304)	45.47	[34035]	0.509[1.356] ^k	184.5	(1.038) ^k
Propane, C ₃ H ₈			0.58962	56.2	76.5	(2.262)	45.20	—	(1.879)	231.1	—
Isobutane, (CH ₃) ₂ CHCH ₃			0.58496	56.4	77.0	(2.239)	45.07	[16930]	[2.67]	261.42	[1900]
Octane, liquid, CH ₃ (CH ₂) ₆ CH ₃			0.57778	56.7	77.7	2.123	44.86	63.8	0.703	398.8	1.397
Paraffin wax, CH ₃ (CH ₂) _{n≈23} CH ₃			0.57275	56.9	78.2	2.087	44.71	48.1	0.93		—
Nylon, type 6 ^l			0.54790	58.5	81.5	1.974	41.84	36.7	1.14		—
Polycarbonate (Lexan) ^m			0.52697	59.5	83.9	1.886	41.46	34.6	1.20		—
Polyethylene terephthalate (Mylar) ⁿ			0.52037	60.2	85.7	1.848	39.95	28.7	1.39		—
Polyethylene ^o			0.57034	57.0	78.4	2.076	44.64	≈47.9	0.92–0.95		—
Polyimide film (Kapton) ^p			0.51264	60.3	85.8	1.820	40.56	28.6	1.42		—
Lucite, Plexiglas ^q			0.53937	59.3	83.0	1.929	40.49	≈34.4	1.16–1.20		≈1.49
Polystyrene, scintillator ^r			0.53768	58.5	81.9	1.936	43.72	42.4	1.032		1.581
Polytetrafluoroethylene (Teflon) ^s			0.47992	64.2	93.0	1.671	34.84	15.8	2.20		—
Polyvinyltolulene, scintillator ^t			0.54155	58.3	81.5	1.956	43.83	42.5	1.032		—
Barium fluoride (BaF ₂)			0.42207	92.0	145	1.303	9.91	2.05	4.89		1.56
Bismuth germanate (BGO) ^u			0.42065	98.2	157	1.251	7.97	1.12	7.1		2.15
Cesium iodide (CsI)			0.41569	102	167	1.243	8.39	1.85	4.53		1.80
Lithium fluoride (LiF)			0.46262	62.2	88.2	1.614	39.25	14.91	2.632		1.392
Sodium fluoride (NaF)			0.47632	66.9	98.3	1.69	29.87	11.68	2.558		1.336
Sodium iodide (NaI)			0.42697	94.6	151	1.305	9.49	2.59	3.67		1.775
Silica Aerogel ^v			0.52019	64	92	1.83	29.83	≈150	0.1–0.3		1.0+0.25ρ
NEMA G10 plate ^w				62.6	90.2	1.87	33.0	19.4	1.7		—

Material	Dielectric constant ($\kappa = \epsilon/\epsilon_0$) () is $(\kappa-1)\times 10^6$ for gas	Young's modulus [10^6 psi]	Coeff. of thermal expansion [$10^{-6}\text{cm}/\text{cm}\cdot^\circ\text{C}$]	Specific heat [cal/g- $^\circ\text{C}$]	Electrical resistivity [$\mu\Omega\text{cm}(@^\circ\text{C})$]	Thermal conductivity [cal/cm- $^\circ\text{C}\cdot\text{sec}$]
H ₂	(253.9)	—	—	—	—	—
He	(64)	—	—	—	—	—
Li	—	—	56	0.86	8.55(0°)	0.17
Be	—	37	12.4	0.436	5.885(0°)	0.38
C	—	0.7	0.6–4.3	0.165	1375(0°)	0.057
N ₂	(548.5)	—	—	—	—	—
O ₂	(495)	—	—	—	—	—
Ne	(127)	—	—	—	—	—
Al	—	10	23.9	0.215	2.65(20°)	0.53
Si	11.9	16	2.8–7.3	0.162	—	0.20
Ar	(517)	—	—	—	—	—
Ti	—	16.8	8.5	0.126	50(0°)	—
Fe	—	28.5	11.7	0.11	9.71(20°)	0.18
Cu	—	16	16.5	0.092	1.67(20°)	0.94
Ge	16.0	—	5.75	0.073	—	0.14
Sn	—	6	20	0.052	11.5(20°)	0.16
Xe	—	—	—	—	—	—
W	—	50	4.4	0.032	5.5(20°)	0.48
Pt	—	21	8.9	0.032	9.83(0°)	0.17
Pb	—	2.6	29.3	0.038	20.65(20°)	0.083
U	—	—	36.1	0.028	29(20°)	0.064

1. R.M. Sternheimer, M.J. Berger, and S.M. Seltzer, Atomic Data and Nuclear Data Tables **30**, 261–271 (1984).
2. S.M. Seltzer and M.J. Berger, Int. J. Appl. Radiat. **33**, 1189–1218 (1982).
3. S.M. Seltzer and M.J. Berger, Int. J. Appl. Radiat. **35**, 665–676 (1984).
 - a. σ_T , λ_T and λ_I are energy dependent. Values quoted apply to high energy range, where energy dependence is weak. Mean free path between collisions (λ_T) or inelastic interactions (λ_I), calculated from $\lambda^{-1} = N_A \sum w_j \sigma_j / A_j$, where N is Avogadro's number and w_j is the weight fraction of the j th element in the element, compound, or mixture. σ_{total} at 80–240 GeV for neutrons ($\approx \sigma$ for protons) from Murthy *et al.*, Nucl. Phys. **B92**, 269 (1975). This scales approximately as $A^{0.77}$. $\sigma_{\text{inelastic}} = \sigma_{\text{total}} - \sigma_{\text{elastic}} - \sigma_{\text{quasielastic}}$; for neutrons at 60–375 GeV from Roberts *et al.*, Nucl. Phys. **B159**, 56 (1979). For protons and other particles, see Carroll *et al.*, Phys. Lett. **80B**, 319 (1979); note that $\sigma_I(p) \approx \sigma_I(n)$. σ_I scales approximately as $A^{0.71}$.
 - b. For minimum-ionizing pions (results are very slightly different for other particles). Minimum dE/dx calculated in 1994, using density effect correction coefficients from Ref. 1. For electrons and positrons see Ref. 3. Ionization energy loss is discussed in Sec. 23.
 - c. From Y.S. Tsai, Rev. Mod. Phys. **46**, 815 (1974); X_0 data for all elements up to uranium are given. Corrections for molecular binding applied for H₂ and D₂. For atomic H, $X_0 = 63.05$ g/cm².
 - d. For molecular hydrogen (deuterium). For atomic H, $X_0 = 63.047$ g cm⁻².
 - e. Density effect constants evaluated for $\rho = 0.0600$ g/cm³ (H₂ bubble chamber?).
 - f. For pure graphite; industrial graphite density may vary 2.1–2.3 g/cm³.
 - g. Standard shielding blocks, typical composition O₂ 52%, Si 32.5%, Ca 6%, Na 1.5%, Fe 2%, Al 4%, plus reinforcing iron bars. The attenuation length, $\ell = 115 \pm 5$ g/cm², is also valid for earth (typical $\rho = 2.15$), from CERN–LRL–RHEL Shielding exp., UCRL–17841 (1968).
 - h. Main components: 80% SiO₂ + 12% B₂O₃ + 5% Na₂O.
 - i. Calculated using Sternheimer's density effect parameterization for $\rho = 2.32$ g cm⁻³. Actual value may be slightly lower.
 - j. For typical fused quartz. The specific gravity of crystalline quartz is 2.64.
 - k. Solid ethane density at -60°C ; gaseous refractive index at 0°C , 546 mm pressure.
 - l. Nylon, Type 6, (NH(CH₂)₅CO)_n
 - m. Polycarbonate (Lexan), (C₁₆H₁₄O₃)_n
 - n. Polyethylene terephthalate, monomer, C₅H₄O₂
 - o. Polyethylene, monomer CH₂=CH₂
 - p. Polyimide film (Kapton), (C₂₂H₁₀N₂O₅)_n
 - q. Polymethylmethacrylate, monomer CH₂=C(CH₃)CO₂CH₃
 - r. Polystyrene, monomer C₆H₅CH=CH₂
 - s. Teflon, monomer CF₂=CF₂
 - t. Polyvinyltoluene, monomer 2-CH₃C₆H₄CH=CH₂
 - u. Bismuth germanate (BGO), (Bi₂O₃)₂(GeO₂)₃
 - v. $n(\text{SiO}_2) + 2n(\text{H}_2\text{O})$ used in Čerenkov counters, $\rho =$ density in g/cm³. From M. Cantin *et al.*, Nucl. Instrum. Methods **118**, 177 (1974).
 - w. G10-plate, typical 60% SiO₂ and 40% epoxy.